

CELLULOSIC AUTOMOTIVE PUTTY

PRODUCT DESCRIPTION

Alkyd resin-based nitrocellulose modified, air drying undercoat putty.



PRODUCT CODE

- GRAY: 1200
- RED: 1212

PRODUCT FEATURES

- Fast drying
- Matt
- Excellent Filling
- High adhesion strength
- Excellent Sanding property
- Long lasting
- Physical and moisture resistance
- Maintain the stability of top coat

AREA OF USE

This product can be used to fill pores and leveling of Wood, Metal, Iron, . . .

RECOMENDED APPLICATION

Surface Preparation:

Before application, the surface should be sanded and made dust and grease free.

Application:

Putty should be applied by scraper or using flexible blade across the desired area 2-3 coats. It can be used Dry or Wet Sanding with sand Mesh Size: P320 – P400.

TECHNICAL INFORMATIONS

TECHNICAL SPECIFICATIONS	
Resin type:	Alkyd+ Nitrocellulose
Color:	Gray and Red
Density (20°C):	1.350 g/cm ³
Solid matter:	60% ± 2 (by weight)
Flash Point:	15°C
Penetration Viscosity:	35-40 mm (@25°C)

DRYING TIMES	
Recoating time:	5-10 min.
Flash off time:	10 min
Dust Dry:	10 min.
Touch Dry:	15 min.
Hard dry:	1-2 hours.

AREA CONSUMPTION

Wet film thickness: 50 – 200 μ
 Dry film thickness: 50 – 100 μ
 Consumption: 5 – 20 (m² /L)

STORAGE AND PACKAGING INFORMATION

Packaging Information: 1 Quart (0.946 Liter) cylinder tin can.

Storage Conditions: It can be stored for 5 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

HEALTH AND SAFETY INFORMATION

Use gloves, work clothes, Protective glasses, and mask .
 Keep out of reach of children, fire and sunlight.

