

CELLULOSIC PRIMER

PRODUCT DESCRIPTION

Alkyd resin-based nitrocellulose modified, air drying Primer.



PRODUCT CODE

- 1226, 1228
- 1010, 1020

PRODUCT FEATURES

- Fast drying
- Matt
- Excellent Hardness
- High adhesion strength
- High Glossy Preservation
- Proper coverage
- Physical and moisture resistance
- Good Sanding Properties

AREA OF USE

This product can be used as under coat or middle layer Primer of wood, Iron and metal.

RECOMENDED APPLICATION

Surface Preparation:

Before application, the surface should be prepared by Sealer and sanded, also must be made dust and grease free.

Application:

Stir the contents inside the can thoroughly and dilute it with NC thinner as needed (30% - 40%). Use gravity feed spray gun with 1.2 to 1.5 mm output or suction feed spray gun with 1.4 to 1.6 mm output and 3 to 4 bar of pressure.

TECHNICAL INFORMATIONS

TECHNICAL SPECIFICATIONS	
Resin type:	Alkyd+ Nitrocellulose
Color:	Gray or Cream
Viscosity(25°C):	110-120 KU
Density (20°C):	1.200 g/cm ³
Solid matter:	58% (by weight)
Flash Point:	15°C

DRYING TIMES	
Recoating time:	5-10 min.
Dust Dry:	20 min.
Touch Dry:	30 min.
Hard dry:	1-2 hours.

AREA CONSUMPTION

Wet film thickness:	50 – 60 μ
Dry film thickness:	20 – 30 μ
Consumption:	8 – 10 (m ² /L)

STORAGE AND PACKAGING INFORMATION

Packaging Information: 1 Quart, 1 Gallon and 4 Gallon cylinder tin can.

Storage Conditions: It can be stored for 5 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

HEALTH AND SAFETY INFORMATION

Use gloves, work clothes, Protective glasses, and mask. Keep out of reach of children, fire and sunlight.

